

## TECHNICAL DATA SHEET : NO MORE DAMP TANKING SLURRY

Issue 2 - 2018 07  
DPTDS05

### PRODUCT DESCRIPTION

NO MORE DAMP tanking slurry is a cementitious waterproof system. When mixed with clean water and applied correctly, it is designed to form a permanent waterproof coating to concrete and masonry and is easily applied by brush, roller or spray.

NO MORE DAMP tanking slurry waterproofs against positive and negative hydrostatic heads of water and is suitable for use, internally, externally, above and below ground. NO MORE DAMP Tanking slurry is also ideal for use in damp-proofing applications.

### TYPICAL USES

Waterproofing of: basements, cellars, foundations, swimming pools, concrete, renders, brickwork, block work structures and lining water tanks, pools and planters etc. Internal & External, above and below ground application.

### ADVANTAGES

- ✓ **PERMANENT WATERPROOFING FOR CONCRETE AND MASONRY**
- ✓ **SUPERIOR BOND STRENGTH**
- ✓ **RESISTS SALT CONTAMINATION IN MASONRY**
- ✓ **SUITABLE FOR INTERNAL & EXTERNAL USE**
- ✓ **SUITABLE FOR USE ABOVE & BELOW GROUND LEVEL**
- ✓ **SAFE TO USE IN CONTACT WITH POTABLE WATER**
- ✓ **EASY TO USE, BRUSH, ROLLER OR SPRAY APPLIED**
- ✓ **RESISTS POSITIVE & NEGATIVE WATER PRESSURE**

### SUBSTRATE PREPARATION

All surfaces must be free from existing coatings or contamination i.e. paint, laitance, dirt etc. All joints must be flush pointed, defects made good and irregular surfaces must be given a trowelled or floated finish with Wykamol's Universal Mortar. If the surface is dry, thoroughly dampen the surface with water prior to application to aid adhesion. If the surface is of a highly



porous nature it is recommended to apply a 1 coat application of Wykamol's SBR at a 1:3 dilution with water, allow approx. 2 hrs drying time prior to application of NO MORE DAMP tanking slurry. Remove all free standing water before application.

Cracks and bolt holes must be cut out and filled solid with NO MORE DAMP Waterstop prior to the application of NO MORE DAMP tanking slurry. Substrates contaminated with high levels of soil or ground water sulphates may require attention.

(Always contact the Wykamol Technical Department if doubt exists).

### MIXING

NO MORE DAMP tanking slurry's consistency can be varied to suit the application method. Recommended water additions:

Pack Size	Brush applied	Trowel applied	Spray applied
20 kg	4.8 - 5.6 litres	3.7 - 4.5 litres	4.2 - 5 litres

Brush applied slurry or Trowel application:

1. Place the recommended amount of clean water into suitable mixing bucket.
2. Using a slow speed electric paddle mixer (400-600 rpm), gradually start to add the powder whilst mixing.
3. Ensure all the powder is added.
4. Mix for approx. 3 minutes to achieve a creamy lump free consistency.
5. If required, add small amount of water to obtain the correct consistency depending on application.

For spray application : Use traditional wet mortar spraying equipment and processes.

## TECHNICAL DATA SHEET : NO MORE DAMP TANKING SLURRY

Issue 2 - 2018 07  
DPTDS05

### APPLICATION

NO MORE DAMP tanking slurry is a minimum 2 coat application system.

Once mixed NO MORE DAMP Tanking slurry has a 30 minutes pot life at 20°C.

Minimum Layer Thickness:

1 st Coat	2nd Coat	Total Thickness (2 coat application)
1.0 mm	1.0 mm	2.0 mm

**Brush applied slurry:** Apply NO MORE DAMP tanking slurry in even layers using a stiff bristled brush or broom on vertical surfaces and a rubber squeegee or stiff bristled brush / broom for horizontal surfaces. It is essential the first coat is brushed well into the surface to ensure a good bond with the substrate. Allow the first coat to set firm (2-16 hours).

Apply a second coat of NO MORE DAMP tanking slurry as soon as the first coat has hardened. Apply the second coat at 90° angle to the first coat.

**Floors:** Special precautions may be necessary to ensure a continuous waterproof barrier at the wall to floor joints and corner joints to avoid sharp changes of angle in the tanking membrane. The joints should be thoroughly raked out, cleaned and wetted prior to application of NO MORE DAMP Universal Mortar.

**Ground level:** Where basement walls finished above the external ground level, the tanking should link up with an effective damp proof course. If basement ceilings are below ground level, the ceiling should also be coated with NO MORE DAMP tanking slurry.

### APPLICATION CONDITIONS & LIMITATIONS

Do not apply NO MORE DAMP tanking slurry to substrates with temperatures below 5°C or if the ambient temperature is below 5°C or expected to fall below 5°C within 24 hrs. Avoid application in direct sunlight. When applying to environments that will contain aquatic life, such as ponds, always finish with NO MORE DAMP Technoseal.

### CURING & VENTILATION

Do not allow NO MORE DAMP tanking slurry to dry out too rapidly. After initial set, moist curing is recommended. Fine mist spray treated area 3 to 4 times daily for a 48 hour period.



It is recommended ventilation is provided as a lack of ventilation may cause condensation to form on the surface of NO MORE DAMP tanking slurry. Protect the coating from excessively fast evaporation in hot conditions or drying winds. If these conditions prevail, fine mist spray the surface regularly.

### OVERCOATING & FINISHING

NO MORE DAMP tanking slurry is suitable for over coating once correctly and thoroughly cured. Plastering should take place using Wykamol's cementitious NO MORE DAMP Renovation Plaster, Universal Mortar or a 1:3 cement: sand plaster with Wykamol's RenderProof incorporated in to protect the Tanking Slurry from impact damage.

Application should be carried out within two days of the final coat being applied.

Gypsum plasters must not be used in direct contact with NO MORE DAMP Tanking slurry.

Wykamol's NO MORE DAMP tanking slurry must not be punctured by wall fixings (e.g. Dry lining work etc.) and a period of 6 months should be allowed before permanent decoration is considered. During this period only use permeable emulsion paints for final decoration purposes. Avoid using impermeable decorative finishes.

### PACK SIZE AND COVERAGE

Product Code	Pack Size	Coverage
NMDTANK20	20 KG	7 m <sup>2</sup>
NMDTANKBUCK20	20 KG	7 m <sup>2</sup>

This is based on an application of No More Damp Tanking Slurry at a thickness of 2 mm (two coat application).

## TECHNICAL DATA SHEET : NO MORE DAMP TANKING SLURRY

Issue 2 - 2018 07  
DPTDS05

### STORAGE

Store in cool, dry conditions off the ground.  
Protect from all sources of moisture and frost.

### SHELF LIFE

6 months from date of manufacture.

### HEALTH AND SAFETY

For further information and advice please contact the Wykamol Technical Department and consult the Safety Data Sheet which is available upon request or can be downloaded from our website.

